Date of revision: 30. Aug. 2021. Replace: 22. Aug. 2019 Version no.: 12

TECHNICAL DATA SHEET

en

Name of product:

Efalyn 0120

Type of product: Styrene-modified alkyd-based paint.

Application: Topcoat for structural steel and containers.

Properties: Quick-drying enamel with superior gloss. Primer is recommended to achieve good

adhesion and protect against corrosion.

Solids: 53 weight % 42 vol. %

Pre-treatment: Sand blasting in accordance with SA 2½ or chemical pre-treatment in accordance with

ISO 8501-1, in addition to, for example, priming with Machine Primer series 0100.

Application:

Method:Recommended viscosity:Thinner:Conventional spraying25 - 30 sec. DIN-cup 4 mm0700-68063Airless/Airmix50 - 55 sec. DIN-cup 4 mm0700-68063This product is developed for electrostatic application. NOTE! If QDE series 0120 is applied twice, the

This product is developed for electrostatic application. NOTE! If QDE series 0120 is applied twice, the second coat should be applied within 4 hours or after 4 days. Failure to observe this may result in the paint

lifting.

Drying:

Dust dry Dry to touch Dry to recoat	Drying time 15 minutes 20 °C 30 minutes 20 °C 1 hour 20 °C		Film thickness - dry 30 - 50 μm 30 - 50 μm 30 - 50 μm		
Recommended coating thickness:	Wet film:	95 µm	Dry film:	40 µm	
Coverage:	Theoretical:	10 m²/ltr			
Shelf-life:	24 Months in an unopened container				
Cleaning:	Tools clean with Synthetic Thinner 0700-68063.				
Note:	Series 0120 is not suitable for application on Shop Primer series 0200 or Machine Primer series 0102.				

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFApaint A/S, Energivej 13, DK-6700 Esbjerg

TLF. +45 75 12 86 00 e-mail: info@efapaint.dk

www.efapaint.dk