

TECHNICAL DATA SHEET

en

Name of product:

Efadeck™ Alkyd Floor Paint 0152

Type of product:	Floor paint based on urethane alkyd. Thins with white spirit.
Application:	Cement and wooden floor coating for private houses. For Industrial floors, Efadeck™ Original 0451 or Efadeck™ H2O Heavy 0699 is recommended.
Properties:	Tough floor paint that is extremely adhesive and water resistant.
Solids:	64 weight % 52 vol. %
Pre-treatment:	The base should be carefully cleaned to remove oil, grease, dirt and paint contaminants. Prime untreated floors with Efadeck™ Alkyd Floor Paint thinned with 20 % white spirit.

Application:

Method:	Recommended viscosity:	Thinner:
Paint Brush	No thinning required	-
Roller	No thinning required	-

White spirit can be used, for thinning, if necessary.

Drying:

	Drying time	Film thickness - dry
Dust dry	1 hour 20 °C	30 - 50 µm
Dry to touch	6 hours 20 °C	30 - 50 µm
Dry to use	16 hours 20 °C	30 - 50 µm
Dry to recoat	4 hours 20 °C	30 - 50 µm
Dry through	4 day(s) 20 °C	30 - 50 µm

Recommended coating thickness: Wet film: 80 µm Dry film: 40 µm

Coverage: Theoretical: 13 m²/ltr.

Storage: Frostfree, cool, and closed.

Shelf-life: 24 Months in an unopened container

Cleaning: Tools clean with white spirit 79120.

Available colors: Grey, white and black.

VOC explanation: Please see the can label for information regarding VOC content.
Product marking: 2004/42/IIA(X)(YY)ZZZ EU directive number: 2004/42/
Directive annex number: IIA
Product subcategory: (X)
VOC content limit value g/l 2010: (YY)
Maximum VOC Content in this product when ready for use, g/l: ZZZ

Note: Efadeck™ H2O Floorpaint series 0567 is our water-bourne alternative.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFApaint A/S, Energivej 13, DK-6700 Esbjerg

TLF. +45 75 12 86 00 e-mail: info@efapaint.dk

www.efapaint.dk