

## TECHNICAL DATA SHEET

en

Name of product:

### Oxyrane One Coat 0472

<b>Type of product:</b>	Vegetable oil based medium solids 2-pack reaction-curing paint containing zinc phosphate, an anti-corrosive pigment. Mix Oxyrane Enamel with Oxyrane Catalyst before using.		
<b>Application:</b>	Single coat painting of agricultural implements and other steel substrates.		
<b>Properties:</b>	Good adhesion to steel. Provides a rich, tough, and robust surface with good chemical resistance.		
<b>Solids:</b>	68 weight %	53 vol. %	Ready to use mixture: Yes
<b>Pre-treatment:</b>	Sandblasting in accordance with SA 2½ or chemical pre-treatment in accordance with ISO 8501-1 is recommended.		

#### Application:

<b>Method:</b>	<b>Recommended viscosity:</b>	<b>Thinner:</b>
Conventional spraying	25-30 sec. DIN-cup 4 mm	0600-91162
Airless/Airmix	25-30 sec. DIN-cup 4 mm	0600-91162

#### 2-Pack Products:

<b>Catalyst</b>	<b>Mixing ratio (volume)</b>	<b>Pot life</b>
0610 - 03329	2 : 1	8 hours 20 °C

#### Drying:

	<b>Drying time</b>	<b>Film thickness - dry</b>
Dry to touch	2 hours 20 °C	40 - 60 µm
Dry to touch	4 hours 20 °C	40 - 60 µm
Forced dry	30 minutes 80 °C	40 - 60 µm

**Recommended coating thickness:** Wet film: 100 µm      Dry film: 50 µm

**Coverage:** Theoretical: 10 m<sup>2</sup>/ltr.

**Storage:** Store cool and dry

**Shelf-life:** 12 Months in an unopened container

**Note:** If the best possible gloss retention is required, we recommend the use of PUR-Enamel, series 0440.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

**EFApaint A/S, Energivej 13, DK-6700 Esbjerg**

TLF. +45 75 12 86 00      e-mail: [info@efapaint.dk](mailto:info@efapaint.dk)

[www.efapaint.dk](http://www.efapaint.dk)