

## TECHNICAL DATA SHEET

en

Name of product:

### FAXE Floor Lacquer 0570

<b>Type of product:</b>	Waterborne lacquer based on acrylic- and polyurethane dispersions.
<b>Application:</b>	Lacquering of wooden floors where wear resistance and easy cleaning is required.
<b>Properties:</b>	Dries quickly and has a tough, elastic film that resists known cleaning agents.
<b>Solids:</b>	36 weight %      30 vol. %
<b>Pre-treatment:</b>	Clean the wood to remove all grease and dirt. The wood should be dry before further treatment. If the floor already has a lacquer it is recommended to sand first. NB! FAXE Floor Lacquer has no adhesion onto UV-lacquered floors.

**Application:**

Method:	Recommended viscosity:	Thinner:
Brush and roller	30-40 sec. DIN-cup 4 mm	water
Spraying	30-40 sec. DIN-cup 4 mm	water

**Drying:**

	Drying time	Film thickness - dry
Dry to touch	30 minutes 20 °C	20 - 25 gram / m <sup>2</sup>
Dry to recoat	90 minutes 20 °C	20 - 25 gram / m <sup>2</sup>
Dry to sand	90 minutes 20 °C	20 - 25 gram / m <sup>2</sup>

**System Specification:**

- 1 x FAXE Floor Lacquer
  - 1 x sanding
  - 1-2 x FAXE Floor Lacquer
- The applications can be done with 1,5 hours drying in between at 20°

<b>Coverage:</b>	Theoretical: 10 m <sup>2</sup> /ltr.
<b>Storage:</b>	Store at minimum. 5°C.
<b>Shelf-life:</b>	12 Months in an unopened container
<b>Cleaning:</b>	Tools clean with water.
<b>VOC explanation:</b>	Product marking: 2004/42/IIA(X)(YY)ZZZ EU directive number: 2004/42/ Directive annex number: IIA Product subcategory: (X) VOC content limit value g/l 2010: (YY) Maximum VOC Content in this product when ready for use, g/l: ZZZ Please see the can label for information regarding VOC content.

**Note:** For information about the gloss - see the label on the packaging.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

**EFApaint A/S, Energivej 13, DK-6700 Esbjerg**

TLF. +45 75 12 86 00      e-mail: [info@efapaint.dk](mailto:info@efapaint.dk)

[www.efapaint.dk](http://www.efapaint.dk)