

TECHNICAL DATA SHEET**en**

Name of product:

H2O Arsinol™ 0575**Type of product:** Vegetable oil-based water-borne wood preservative.**Application:** Wood preservative for new exterior woodwork. Should not be used for larger surfaces in residential or living areas.**Properties:** Good adhesion to wood, exterior durability.**Solids:** 61 weight % 49 vol. %**Pre-treatment:** Clean dirty woodwork with a stiff brush. The wood should be clean and dry before further painting. (Max. moisture content 10-15 %).**Application:****Method:**

Paint Brush

Water can be used if necessary, for thinning.

Recommended viscosity:

No thinning required

Thinner:

-

Drying:

	Drying time	Film thickness - dry
Dust dry	30 minutes 20 °C	30 - 50 µm
Dry to touch	90 minutes 20 °C	30 - 50 µm
Dry to recoat	2 hours 20 °C	30 - 50 µm

System Specification:

1. Treatment: Arsinol™ H2O Primer, series 0572
2. Treatment: Arsinol™ H2O, series 0575

Recommended coating thickness: Wet film: 90 µm Dry film: 40 µm**Coverage:** Theoretical: 12 m²/ltr.**Storage:** Store above 5° C.**Shelf-life:** 12 Months in an unopened container**Cleaning:** Tools clean with water.**Available colors:** Please see our color card for information on the color range.

VOC explanation: Please see the can label for information regarding VOC content.
Product marking: 2004/42/IIA(X)(YY)ZZZ EU directive number: 2004/42/
Directive annex number: IIA
Product subcategory: (X)
VOC content limit value g/l 2010: (YY)
Maximum VOC Content in this product when ready for use, g/l: ZZZ

Note: H2O Arsinol™ must not be applied in wet weather or at temperatures below 10° C.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFApaint A/S, Energivej 13, DK-6700 Esbjerg**TLF. +45 75 12 86 00****e-mail: info@efapaint.dk****www.efapaint.dk**