

TECHNICAL DATA SHEET

en

Name of product:

EFAMetal EFAspray 0790

Type of product: Alkyd-based spray paint that uses propan/butan as a propellant.

Application: Touch-up paint for metal substrates.

Properties: Fast air-drying.

Solids: 25 weight % 18 vol. %

Pre-treatment: The surface must be free of grease, oil and rust contaminants. If priming is required, EFAMetal EFAspray Primer 0790 is recommended.

Application:

Method:

Recommended viscosity:

Thinner:

-

NOTE! If EFAMetal EFAspray 0790 is applied twice, the second coat should be applied within 4 hours or after 4 days. Failure to do this could result in the paint lifting.

Drying:

	Drying time	Film thickness - dry
Dust dry	5 - 10 minutes 20 °C	-
Dry to touch	30 minutes 20 °C	-
Dry to recoat	1 hour 20 °C	-

Recommended coating thickness: Wet film: 100 µm Dry film: 18 µm

Coverage: Theoretical: 10 m²/ltr.

Storage: Store cool and dry

Shelf-life: 24 Months in an unopened container

Note: EFAMetal EFAspray 0790 is not suitable for application on Shop Primer, series 0200 or EFAMetal Machine Primer series 0102. When heat resistance to 400°C is required we recommend EFAMetal EFAspray 0790-72041.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFApaint A/S, Energivej 13, DK-6700 Esbjerg

TLF. +45 75 12 86 00 e-mail: info@efapaint.dk

www.efapaint.dk