

**TECHNICAL DATA SHEET****en**

Name of product:

**Efaspray 0790****Type of product:** Alkyd-based spray paint that uses propan/butan as a propellant.**Application:** Touch-up paint for metal substrates.**Properties:** Fast air-drying.**Solids:** 25 weight % 18 vol. %**Pre-treatment:** The surface must be free of grease, oil and rust contaminants. If priming is required, Efaspray Primer series 0790 is recommended.**Application:****Method:****Recommended viscosity:****Thinner:**

-

NOTE! If Efaspray is applied twice, the second coat should be applied within 4 hours or after 4 days. Failure to do this could result in the paint lifting.

**Drying:**

	<b>Drying time</b>	<b>Film thickness - dry</b>
Dust dry	5 - 10 minutes 20 °C	-
Dry to touch	30 minutes 20 °C	-
Dry to recoat	1 hour 20 °C	-

**Recommended coating thickness:** Wet film: 100 µm Dry film: 18 µm**Coverage:** Theoretical: 10 m<sup>2</sup>/ltr.**Storage:** Store cool and dry**Shelf-life:** 24 Months in an unopened container**Note:** Series 0790 is not suitable for application on Shop Primer, series 0200 or Machine Primer series 0102. When heat resistance to 400°C is required we recommend Efaspray 0790-72041.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

**EFApaint A/S, Energivej 13, DK-6700 Esbjerg**

TLF. +45 75 12 86 00

e-mail: [info@efapaint.dk](mailto:info@efapaint.dk)[www.efapaint.dk](http://www.efapaint.dk)