

## TECHNICAL DATA SHEET

en

Name of product:

### EFAcombi OX 472 one coat

<b>Type of product:</b>	Vegetable oil based medium solids 2-pack reaction-curing paint containing zinc phosphate, an anti-corrosive pigment. Mix EFAcombi OX 472 one coat with OX hardener 0610 03329 before using.		
<b>Application:</b>	Single coat painting of agricultural implements and other steel substrates.		
<b>Properties:</b>	Good adhesion to steel. Provides a rich, tough, and robust surface with good chemical resistance.		
<b>Solids:</b>	68 weight %	53 vol. %	Ready to use mixture: Yes
<b>Pre-treatment:</b>	Sandblasting in accordance with SA 2½ or chemical pre-treatment in accordance with ISO 8501-1 is recommended.		

#### Application:

Method:	Recommended viscosity:	Thinner:
Conventional spraying	25-30 sec. DIN-cup 4 mm	0600-91162
Airless/Airmix	25-30 sec. DIN-cup 4 mm	0600-91162

#### 2-Pack Products:

Catalyst	Mixing ratio (volume)	Pot life
0610 - 03329	2 : 1	8 hours 20 °C

#### Drying:

	Drying time	Film thickness - dry
Dry to handle	2 hours 20 °C	40 - 60 µm
Dry to touch	4 hours 20 °C	40 - 60 µm
Forced drying	30 minutes 80 °C	40 - 60 µm

**Recommended coating thickness:** Wet film: 100 µm      Dry film: 50 µm

**Coverage:** Theoretical: 10 m<sup>2</sup>/ltr.

**Storage:** Store cool and dry

**Shelf-life:** 12 Months in an unopened container

**Note:** If the best possible gloss retention is required, we recommend the use of EFAtop PU 440 enamel.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

**EFApaint A/S, Energivej 13, DK-6700 Esbjerg**

TLF. +45 75 12 86 00      e-mail: [info@efapaint.dk](mailto:info@efapaint.dk)

[www.efapaint.dk](http://www.efapaint.dk)