FAXE Universal Lve THIX 0251

TECHNICAL DATA SHEET

Name of product:

Type of product:	White lye base	White lye based on vegetable oils, naturel wax, pigments and sodium hydroxide.		
Application:		FAXE Universal Lye THIX, is a lye, which slows down the yellowing process of wood in a chemical way.		
Properties:	Lye slows dow	Lye slows down the yellowing process - can be applied to roller and spray equipment.		
Solids:	8 weight %	8 vol. %		
Pre-treatment:	The wood has	The wood has to be sanded, clean and dry.		
Application:				
Method:	F	Recommended viscosity:	Thinner:	
Industrial roller coater	Ν	lo thinning required	-	
Spraying	Ν	lo thinning required	-	
FAXE Universal Lye TH the industry.	HIX is made thixotro	opic so that it can be applied to the ro	oller and spray equipment in	

20 - 25 gram / m²

20 - 25 gram / m²

System Specification:

1x FAXE Universal Lye THIX

The product has to be stirred before and during use.

5 hours 20 °C

5 minutes 40 °C

After Care:

Dry to touch Forced drying

Subsequently, the surface can be treated with oil, hardwax, Invisioil and the like, depending on the surface and the effect you want.

Aftercare: Dust and loose dirt can be removed with a brush or vacuum cleaner. We recommend FAXE Active Care or FAXE Wooden Floor Soap for cleaning. To renovate, clean the surface with FAXE Intensive Cleaner and then apply a coat of FAXE Woodcare Oil or another FAXE Oil.

Coverage:	Theoretical: 10 m²/ltr.		
Storage:	Store above 5° C.		
Shelf-life:	12 Months in an unopened container		
Cleaning:	The tools should be cleaned with water.		

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFApaint A/S, Energivej 13, DK-6700 Esbjerg

TLF. +45 75 12 86 00 e-mail: info@efapaint.dk

www.efapaint.dk

Page 1/1 Version no.: 3

en