Efadeck[™] H2O Floor Paint 0567

TECHNICAL DATA SHEET

Name of product:

Type of product:	Water-borne p	aint based	l on urethane- an	d acrylic dispe	rsion.
Application:	Wooden and concrete floor coating, where a strong, dust-free surface is required.				
Properties:	Good adhesion to wood and concrete. Can be applied on painted floors without risk of lifting.				
Solids:	46 weight %	37 vol.	%		
Pre-treatment:	 WOODEN FLOORS: The floor must be clean and free from dust, grease and soap residues. Clean with Cleaner or FAXE Intensive Cleaner. Subsequent coatings require light sanding before application. CONCRETE FLOORS: The floor must be clean and free of dust. If the floor is glazed and has an impermeable surface, sanding treatment is recommended. After this, apply Efadeck™ H2O Floor Paint twice. The first application requires 10 % thinning with water, and the second requires no thinning. NB! By painting on self-compacting concrete / self levelling compound the first layer has to be diluted 50 % with water and the second layer by 25 %. The toplayer must not be diluted. 				
Application:					
Method:	R	Thinner:			
Brush and roller	No thinning required				
Water can be used to cle	an paint equipme	nt and, if n	ecessary, for thin	ning.	
Drvina:					
Drying:			Film this lances	-las -	
	Drying time		Film thickness	- dry	
Dust dry	1 hour 20 °C		30 - 50 µm	- dry	
Dust dry Dry to touch	1 hour 20 °C 4 hours 20 °C		30 - 50 μm 30 - 50 μm	- dry	
Dust dry Dry to touch Dry to recoat	1 hour 20 °C 4 hours 20 °C 4 hours 20 °C		30 - 50 μm 30 - 50 μm 30 - 50 μm	- dry	
Dust dry Dry to touch	1 hour 20 °C 4 hours 20 °C		30 - 50 μm 30 - 50 μm	- dry	
Dust dry Dry to touch Dry to recoat Dry to use	1 hour 20 °C 4 hours 20 °C 4 hours 20 °C 4 days 20 °C	110 µm	30 - 50 μm 30 - 50 μm 30 - 50 μm 30 – 50 μm	- dry 40 μm	
Dust dry Dry to touch Dry to recoat Dry to use Dry through Recommended coating thickness:	1 hour 20 °C 4 hours 20 °C 4 hours 20 °C 4 days 20 °C 1 week 20 °C	110 μm 9 m²/ltr.	30 - 50 μm 30 - 50 μm 30 - 50 μm 30 – 50 μm 30 – 50 μm	-	
Dust dry Dry to touch Dry to recoat Dry to use Dry through Recommended coating thickness: Coverage:	1 hour 20 °C 4 hours 20 °C 4 hours 20 °C 4 days 20 °C 1 week 20 °C Wet film:	9 m²/ltr.	30 - 50 μm 30 - 50 μm 30 - 50 μm 30 – 50 μm 30 – 50 μm	-	
Dust dry Dry to touch Dry to recoat Dry to use Dry through Recommended coating	1 hour 20 °C 4 hours 20 °C 4 hours 20 °C 4 days 20 °C 1 week 20 °C Wet film: Theoretical:	9 m²/ltr. ° C.	30 - 50 μm 30 - 50 μm 30 - 50 μm 30 - 50 μm 30 - 50 μm	-	

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFApaint A/S, Energivej 13, DK-6700 Esbjerg

TLF. +45 75 12 86 00

e-mail: info@efapaint.dk

www.efapaint.dk

Page 1/1 Version no.: 9

en