

TECHNICAL DATA SHEET

en

Name of product:

EFAMetal Ploughshare Varnish 0124

Type of product:	Transparent, blue lacquer based on styrene modified alkyd.
Application:	Temporary protection of steel, such as plough shares and harrow teeth.
Properties:	Dries quickly and produces an attractive finish.
Solids:	44 weight % 40 vol. %
Pre-treatment:	The surface must be free of grease, oil and rust contaminants.

Application:

Method:	Recommended viscosity:	Thinner:
Conventional spraying	25-30 sec. DIN-cup 4 mm	0700-68063
Airless/Airmix	50-55 sec. DIN-cup 4 mm	0700-68063
Paint Brush	No thinning required	

NOTE! If EFAMetal Ploughshare Varnish is applied twice, the second coat should be applied within 4 hours or after 4 days. Failure to do this could result in the paint lifting.

Drying:

	Drying time	Film thickness - dry
Dust dry	15 minutes 20 °C	20 - 40 µm
Dry to touch	30 minutes 20 °C	20 - 40 µm
Dry to recoat	1 hour 20 °C	20 - 40 µm

Recommended coating thickness: Wet film: 75 µm Dry film: 30 µm

Coverage: Theoretical: 13 m²/ltr.

Storage: Store cool and dry

Shelf-life: 12 Months in an unopened container

Cleaning: Tools clean with Synthetic Thinner 0700-68063.

Note: EFAtop AK 551 H2O Enamel is our water-borne alternative.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFAPaint A/S, Energivej 13, DK-6700 Esbjerg

TLF. +45 75 12 86 00 e-mail: info@efapaint.dk

www.efapaint.dk