

TECHNICAL DATA SHEET**en****Name of product:****FAXE White Lye 0287****Type of product:** White lye based on vegetable oils, naturel wax, pigments and sodium hydroxide.**Application:** Faxe White Lye can be used for all types of wood, but are best mainly for light wood. The colour will depend on the type of wood.**Properties:** Faxe White Lye stops the naturel yellowing of the wood and gives untreated wood a light, whitewashed surface with a visible structure.**Solids:** 8 weight % 8 vol. %**Pre-treatment:** The wood has to be sanded, clean and dry.
Dirt has to be removed with FAXE Intensive Cleaner.
1. The product has to be shaken/stirred before and during use.
2. The Lye is applied evenly and undiluted with a brush or a lambswoolswab at the longitudinal of the wood. Overlaps has to be removed while the wood is still wet. For an intensive effect, the treatment can be repeated after the wood is dry.**Application:**

| Method: | Recommended viscosity: | Thinner: |
|-----------------|-------------------------------|-----------------|
| Paint Brush | 10 sec. DIN-cup 4 mm | water |
| Lambswool swab. | 10 sec. DIN-cup 4 mm | water |

Drying:

| | Drying time | Film thickness - dry |
|--------------|--------------------|-------------------------------|
| Dry to touch | 5 hours 20 °C | 20 - 25 gram / m ² |
| Forced dry | 5 minutes 40 °C | 20 - 25 gram / m ² |

System Specification:

If needed 1x Faxe Industrial Lye
 If needed 1x sanding
 1x Faxe High Solid Micro Oil
 Hereafter can treatment with Faxe Industrial Oilcare be done.

Coverage: Theoretical: 10 m²/ltr.**Storage:** Store above 5° C.**Shelf-life:** 12 Months in an unopened container**Cleaning:** The tools should be cleaned with water.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFApaint A/S, Energivej 13, DK-6700 Esbjerg

TLF. +45 75 12 86 00

e-mail: info@efapaint.dkwww.efapaint.dk