

TECHNICAL DATA SHEET**en**

Name of product:

Efadeck® PolyMarine component I 0465

Type of product: 2-pack polyurethane coating. Before use, mix with PolyMarine component II, 0616. PolyMarine component III, 0685 98227 may be added.

Application: Solvent-free coating for e.g. ship's ramps.

Properties: Weatherproof and hard wearing. Fast curing.

Solids: 100 weight % 100 vol. % Ready to use mixture: Yes

Pre-treatment: The base surface should be clean and free of dust.

Drying:

	Drying time	Film thickness - dry
Dry to use	24 hours 20 °C	-
Fully cured	3 day(s) 20 °C	-

Recommended coating thickness: Wet film: 1.000 µm Dry film: 1.000 µm

Coverage: Theoretical: 1 m²/ltr.

Storage: Store at minimum. 5°C.

Shelf-life: 12 Months in an unopened container

Note: Mixing ratio: Please see the can label for information. Potlife 30 minutes @ 20°C.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFApaint A/S, Energivej 13, DK-6700 Esbjerg

TLF. +45 75 12 86 00

e-mail: info@efapaint.dkwww.efapaint.dk