FFAcombi PU 443 one coat

TECHNICAL DATA SHEET

Name of product:

Type of product:	2-pack acrylic/polyurethane paint containing zinc phosphate, an anti-corrosive pigment.			
Application:	Single-layer paint for coating metal.			
Properties:	Outstanding toughness and protection against corrosion as well as chemical and weather resistance.			
Solids:	60 weight % 46 vol. % Ready to use		Ready to use mix	kture: Yes
Pre-treatment:	Sandblasting in accordance with SA 2 ¹ / ₂ or chemical pre-treatment in accordance with ISO 8501-1 is recommended.			
Application:				
Method:	Recomme	nded viscosity:		Thinner:
Airless/Airmix	40-45 sec. DIN-cup 4 mm			-en-
2-Pack Products:				
PART B 0610 19020	Mixing ratio (volume) 7 : 1		Pot life 8 hours 20 °C	
Drying:				
	Drying time Film thickness - dr		s - dry	
Dust dry	1 hour 20 °C	50 - 70 µm	-	
	2 hours 20 °C	50 - 70 µm		
Dry to touch		oo ropin		
Recoat before	7 day(s) 20 °C	50 - 70 µm		
5		•		
Recoat before	7 day(s) 20 °C	50 - 70 μm 50 - 70 μm	60 µm	
Recoat before Forced drying Recommended coating	7 day(s) 20 °C 30 minutes 60 °C	50 - 70 μm 50 - 70 μm	60 µm	
Recoat before Forced drying Recommended coating thickness:	7 day(s) 20 °C 30 minutes 60 °C Wet film: 130 μm	50 - 70 μm 50 - 70 μm	60 µm	
Recoat before Forced drying Recommended coating thickness: Coverage:	7 day(s) 20 °C 30 minutes 60 °C Wet film: 130 μm Theoretical: 8 m²/ltr.	50 - 70 μm 50 - 70 μm Dry film:	60 µm	

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFApaint A/S, Energivej 13, DK-6700 Esbjerg

TLF. +45 75 12 86 00 e-mail: info@efapaint.dk

www.efapaint.dk

Page 1/1 Version no.: 6

en